

AUS

Acrylic-Urethane Sealer

Sealer for LikeNu and Polymer Concrete Applications
Keeps moisture and chemicals out of concrete
Primer for Flex-Clear Urethane Applications
Water Based Acrylic-Urethane Blend :: Safe to use.
No harmful solvents.

Application

Can be diluted with water up to 50:50. One coat for Primer & Light Sealing Applications. Apply to a clean, dry surface with roller, brush or spray application. Keep coats thin, no puddling. Dry to touch in one hour. Sealer properties will improve over a week's full cure cycle. We recommend using Aziridine Cross-linker to improve the cured film properties. If doing multiple coats use crosslinker only in final coat. Use glass beads for increased hardness. Contact us for further information.

Acrylic-Urethane liquid properties --- specifications	
Appearance	Blue-white liquid
Solids:	33% +/-2%
Viscosity: (Bookfield-lvf-72deg.F)	80cps-300 cps
PH:	7.5-8
Flashpoint (SETAFLASH cc)	None
Weight/gal	8.67 lbs.
VOC	<0.40 lb. / gal. (<48 g/l)
Solvents:	triethylamine <.25% Butyl cellusolve 1.1%
Cure:	aziridine, polyfunctional 28-84 grams/ gallon
TSCA status:	all components listed on TSCA inventory

Physical Properties of Acrylic Urethane Sealer (cured 7 days at ambient conditions)	
100% Modulus	6000 psi strength
Tensile Strength	8500 psi
Elongation	100
Sward hardness	65

WonderPaint Inc
249 Old Zion Church Road
Woodburn, KY 42170
ph/fax 270 529-0056
www.wonderpaint.com